



Aluminum coating with fiberglass support, absorbent M-1 F-1 fiberboard.

Measurements according to UNE-EN ISO 140-3 standard (December 1995)
 Acoustic Isolation of Construction Materials in Laboratory Measurements.
 Corresponds completely with ISO 140-3(1995) standard.
 Cancels and substitutes UNE 74-040/3 (1984) standard.
 Calculations according to NBECA88.

Type	Code	SELF-ADHESIVE	Rw (dB)	Weight (kg)
MARINE	28411	-	33	7,2

TECHNICAL CHARACTERISTICS

- Thicknesses: 50mm
- format: sheets of 1000 x 610 mm


FORMATS

APPLICATIONS

Thermal insulation, M-1 flame retardant behavior, very good smoke behavior, not very good absorbent, but very good insulation.

ACOUSTIC PROPERTIES

Transmission Loss (dB)



Absorption Coefficient

