

Akustikabsorber

PI



White coloured fibreglass facing and absorbing polyurethane foam.

Measurements according to UNE-EN ISO 140-3 standard (December 1995)
Acoustic Isolation of Construction Materials in Laboratory Measurements.
Corresponds completely with ISO 140-3(1995) standard.
Cancels and substitutes UNE 74-040/3 (1984) standard.
Calculations according to NBCEA88.

| Type | Code | SELF-ADHESIVE | Rw (dB) | Weight (kg) |
|---------------|-------|---------------|---------|-------------|
| PI-15 sheet | 26019 | - | 18 | 0,663 |
| PI-15 A sheet | 26180 | ☐ | 18 | 1,113 |
| PI-15 roll | 26016 | - | 18 | 0,663 |
| PI-15 A roll | 26183 | ☐ | 18 | 1,113 |
| PI-25 sheet | 26020 | - | 18 | 0,965 |
| PI-25 A sheet | 26181 | ☐ | 18 | 1,415 |
| PI-25 roll | 26017 | - | 18 | 0,965 |
| PI-25 A roll | 26069 | ☐ | 18 | - |
| PI-40 sheet | 26021 | - | 19 | 1,418 |
| PI-40 A sheet | 26182 | ☐ | 19 | 1,868 |
| PI-40 roll | 26018 | - | 19 | 1,418 |
| PI-40 A roll | 26184 | ☐ | 19 | 1,868 |

TECHNICAL CHARACTERISTICS

— Composition

White coloured fibreglass facing and absorbing polyurethane foam.

— Thicknesses

15mm 25mm 40mm

FORMATS

— Sheets

1200x1000 mm
15mm thick, 8 Sheets per box.
25mm thick, 5 Sheets per box.
40mm thick, 3 Sheets per box.

— Rolls

1500mm wide x approx. 20m long

APPLICATIONS

Thermal insulation, good resistance to hydrocarbon damage and not very good acoustic absorber but good isolator.

Akustikabsorber

PI

ACOUSTIC PROPERTIES

